

杭州科德磁业有限公司

HANGZHOU KEDE MAGNETICS COMPONENTS CO., LTD.

中国浙江省杭州市桐庐县樟青塘路168号, 邮编: 311500

No.168 Zhangqingtang Road, Tonglu, Hangzhou 311500, China.

电话/tel: +86 571 64242689 传真/fax: +86 571 64242687, 电子邮件/email: [info@kedemagnetics.com](mailto:info@kedemagnetics.com)



Typical Magnetic Properties of Compression Molding NdFeB Magnets (压制成型钕铁硼磁铁典型磁性能表)

类别 Item	牌号 Grade	剩磁 Remanence induction		矫顽力 Coercive force		内禀矫顽力 Intrinsic Coercive force		最大磁能积 Maximum Energy product		工作温度 Working Temperat ure	密度 Density	平均可逆温度 系数 Temperature Coefficient of B
		B <sub>r</sub>		H <sub>cB</sub>		H <sub>cJ</sub>		(BH) <sub>max</sub>		T <sub>w</sub>	ρ	α
		T	KGs	KA/m	KOe	KA/m	KOe	KJ/m <sup>3</sup>	MGOe	°C	g/cm <sup>3</sup>	%/°C
压制成型 钕铁硼 Compression Molding NdFeB Magnet	KBM-2	0.30~0.40	3.0-4.0	160~240	2.0~3.0	480~640	6.0~8.0	16~24	2.0~3.0	≤120	4.5~6.0	-0.12
	KBM-4	0.40~0.50	4.0~5.0	240~320	3.0~4.0	560~720	7.0~9.0	32~44	4.0~5.5	≤120	5.2~6.0	-0.11
	KBM-6	0.55~0.63	5.5~6.3	320~400	4.0~5.0	480~640	6.0~8.0	48~60	6.0~7.5	≤120	5.5~6.0	-0.11
	KBM-8	0.65~0.68	6.5~6.8	360~440	4.5~5.5	640~800	8.0~10.0	64~72	8.0~9.0	≤150	5.8~6.1	-0.1
	KBM-8H	0.60~0.65	6.0~6.5	400~480	5.0~6.0	1120~1280	14.0~16.0	60~68	7.5~8.5	≤160	5.8~6.2	-0.1
	KBM-8L	0.65~0.68	6.5~6.8	400~480	5.0~6.0	900~1120	11.0~14.0	64~72	8.0~9.0	≤160	5.8~6.2	-0.1
	KBM-9	0.60~0.68	6.0~6.8	400~480	5.0~6.0	640~800	8.0~10.0	68~72	8.5~9.0	≤150	5.8~6.2	-0.1
	KBM-10	0.68~0.73	6.8~7.3	400~480	5.0~6.0	640~800	8.0~10.0	76~84	9.5~10.5	≤150	5.8~6.2	-0.1
	KBM-12	0.71~0.75	7.1~7.5	440~520	5.5~6.5	720~800	9.0~10.0	84~96	10.5~12.0	≤150	6.0~6.2	-0.1
	KBM-12L	0.72~0.76	7.2~7.6	400~480	5.0~6.0	480~640	6.0~8.0	84~96	10.5~12.0	≤140	6.0~6.2	-0.12

at the Forefront of Magnetics Solutions