

Datasheet of Compression Molding NdFeB at Room Temperature (压制成型钕铁硼的磁性能 (室温))

类别 Item	牌号 Grade	剩磁 Remanence induction		矫顽力 Coercive force		内禀矫顽力 Intrinsic Coercive force		最大磁能积 Maximum Energy product		工作温度 Working Temperature	密度 Density	平均可逆 温度系数 temperature coefficient of Br
		B _r		H _{cB}		H _{cJ}		(BH) _{max}		T _w	ρ	α
		T	KGs	KA/m	KOe	KA/m	KOe	KJ/m ³	MGOe	°C	g/cm ³	%/°C
压制成型 钕铁硼 Compression Molding NdFeB Magnet	KBM-2	0.30~0.40	3.0~4.0	160~240	2.0~3.0	480~640	6.0~8.0	16~24	2.0~3.0	≤120	4.5~6.0	-0.12
	KBM-4	0.40~0.50	4.0~5.0	240~320	3.0~4.0	560~720	7.0~9.0	32~44	4.0~5.5	≤120	5.2~6.0	-0.11
	KBM-6	0.55~0.63	5.5~6.3	320~400	4.0~5.0	480~640	6.0~8.0	48~60	6.0~7.5	≤120	5.5~6.0	-0.11
	KBM-8	0.65~0.68	6.5~6.8	360~440	4.5~5.5	640~800	8.0~10.0	64~72	8.0~9.0	≤150	5.8~6.1	-0.10
	KBM-8H	0.60~0.65	6.0~6.5	400~480	5.0~6.0	1120~1280	14.0~16.0	60~68	7.5~8.5	≤160	5.8~6.2	-0.10
	KBM-8L	0.65~0.68	6.5~6.8	400~480	5.0~6.0	900~1120	11.0~14.0	64~72	8.0~9.0	≤160	5.8~6.2	-0.10
	KBM-9	0.60~0.68	6.0~6.8	400~480	5.0~6.0	640~800	8.0~10.0	68~72	8.5~9.0	≤150	5.8~6.2	-0.10
	KBM-10	0.68~0.73	6.8~7.3	400~480	5.0~6.0	640~800	8.0~10.0	76~84	9.5~10.5	≤150	5.8~6.2	-0.10
	KBM-12	0.71~0.75	7.1~7.5	440~520	5.5~6.5	720~800	9.0~10.0	84~96	10.5~12.0	≤150	6.0~6.2	-0.10
	KBM-12L	0.72~0.76	7.2~7.6	400~480	5.0~6.0	480~640	6.0~8.0	84~96	10.5~12.0	≤140	6.0~6.2	-0.12