

杭州科德磁业有限公司

HANGZHOU KEDE MAGNETICS COMPONENTS CO., LTD.

中国浙江省杭州市桐庐县樟青塘路168号, 邮编: 311500

No.168 Zhangqingtang Road, Tonglu, Hangzhou 311500, China.

电话/tel: +86 571 64242689 传真/fax: +86 571 64242687,

电子邮件/email: info@kedemagnetics.com



Typical Magnetic Properties of Sintered NdFeB Magnets (烧结钕铁硼磁铁典型磁性能表)

牌号 Grade	剩磁 Remanence induction		矫顽力 Coercive force		内禀矫顽力 Intrinsic Coercive force		最大磁能积 Maximum Energy product		工作温度 Working Temperature	密度 Density
	B _r		H _{cB}		H _{cJ}		(BH) _{max}		T _w	ρ
	T	KGs	KA/m	KOe	KA/m	KOe	KJ/m ³	MGOe	°C	g/cm ³
一般工艺 General Process										
N38	1.23-1.30	12.3-13.0	≥876	≥11	≥955	≥12	287-318	36-40	≤80	≥7.5
N40	1.26-1.32	12.6-13.2	≥876	≥11	≥955	≥12	302-334	38-42	≤80	≥7.5
N42	1.29-1.35	12.9-13.5	≥876	≥11	≥955	≥12	318-350	40-44	≤80	≥7.5
N45	1.32-1.38	13.2-13.8	≥876	≥11	≥955	≥12	334-366	42-46	≤80	≥7.5
N48	1.37-1.43	13.7-14.3	≥876	≥11	≥955	≥12	358-390	45-49	≤80	≥7.5
N50	1.40-1.45	14.0-14.5	≥876	≥11	≥955	≥12	374-406	47-51	≤80	≥7.5
N52	1.42-1.48	14.2-14.8	≥836	≥10.5	≥876	≥11	390-422	49-53	≤80	≥7.5
N55	1.46-1.51	14.6-15.1	≥860	≥10.8	≥955	≥12	406-438	51-55	≤80	≥7.5
N38M	1.23-1.30	12.3-13.0	≥915	≥11.5	≥1114	≥14	287-318	36-40	≤100	≥7.5
N40M	1.26-1.32	12.6-13.2	≥939	≥11.8	≥1114	≥14	302-334	38-42	≤100	≥7.5
N42M	1.29-1.35	12.9-13.5	≥963	≥12.1	≥1114	≥14	318-350	40-44	≤100	≥7.5
N45M	1.32-1.38	13.2-13.8	≥987	≥12.4	≥1114	≥14	334-366	42-46	≤100	≥7.5
N48M	1.37-1.43	13.7-14.3	≥1019	≥12.8	≥1114	≥14	358-390	45-49	≤100	≥7.5
N50M	1.40-1.45	14.0-14.5	≥1043	≥13.1	≥1114	≥14	374-406	47-51	≤100	≥7.5
N52M	1.42-1.48	14.2-14.8	≥1059	≥13.3	≥1114	≥14	390-422	49-53	≤100	≥7.5
N54M	1.46-1.51	14.6-15.1	≥995	≥12.5	≥1035	≥13	406-438	51-55	≤100	≥7.5
N35H	1.17-1.24	11.7-12.4	≥876	≥11.0	≥1353	≥17	263-295	33-37	≤120	≥7.5
N38H	1.23-1.30	12.3-13.0	≥915	≥11.5	≥1353	≥17	286-318	36-40	≤120	≥7.5
N40H	1.26-1.32	12.6-13.2	≥939	≥11.8	≥1353	≥17	302-334	38-42	≤120	≥7.5
N42H	1.29-1.35	12.9-13.5	≥963	≥12.1	≥1353	≥17	318-350	40-44	≤120	≥7.5
N45H	1.32-1.38	13.2-13.8	≥987	≥12.4	≥1353	≥17	334-366	42-46	≤120	≥7.5
N48H	1.37-1.43	13.7-14.3	≥1011	≥12.7	≥1353	≥17	358-390	45-49	≤120	≥7.5
N50H	1.40-1.45	14.0-14.5	≥1027	≥12.9	≥1353	≥17	374-406	47-51	≤120	≥7.5
N52H	1.42-1.48	14.2-14.8	≥1059	≥13.3	≥1353	≥17	390-422	49-53	≤120	≥7.5
N33SH	1.14-1.21	11.4-12.1	≥852	≥10.7	≥1592	≥20	247-279	31-35	≤150	≥7.5
N35SH	1.17-1.24	11.7-12.4	≥876	≥11.0	≥1592	≥20	263-295	33-37	≤150	≥7.5
N38SH	1.23-1.29	12.3-12.9	≥915	≥11.5	≥1592	≥20	287-318	36-40	≤150	≥7.5
N40SH	1.26-1.32	12.6-13.2	≥939	≥11.8	≥1592	≥20	302-334	38-42	≤150	≥7.5
N42SH	1.29-1.35	12.9-13.5	≥963	≥12.1	≥1592	≥20	318-350	40-44	≤150	≥7.5
N45SH	1.32-1.38	13.2-13.8	≥987	≥12.4	≥1592	≥20	334-366	42-46	≤150	≥7.5

to be continued(接下页)

杭州科德磁业有限公司

HANGZHOU KEDE MAGNETICS COMPONENTS CO., LTD.

中国浙江省杭州市桐庐县樟青塘路168号, 邮编: 311500

No.168 Zhangqingtang Road, Tonglu, Hangzhou 311500, China.

电话/tel: +86 571 64242689 传真/fax: +86 571 64242687,

电子邮件/email: info@kedemagnetics.com



Typical Magnetic Properties of Sintered NdFeB Magnets (烧结钕铁硼磁铁典型磁性能表)

牌号 Grade	剩磁 Remanence induction		矫顽力 Coercive force		内禀矫顽力 Intrinsic Coercive force		最大磁能积 Maximum Energy product		工作温度 Working Temperature	密度 Density
	B _r		H _{cB}		H _{cJ}		(BH) _{max}		T _w	ρ
	T	KGs	KA/m	KOe	KA/m	KOe	KJ/m ³	MGOe	°C	g/cm ³
N48SH	1.37-1.43	13.7-14.3	≥1011	≥12.7	≥1592	≥20	358-390	45-49	≤150	≥7.5
N50SH	1.40-1.45	14.0-14.5	≥1027	≥12.9	≥1592	≥20	374-406	47-51	≤150	≥7.5
N52SH	1.42-1.48	14.2-14.8	≥1035	≥13	≥1512	≥19	390-422	49-53	≤150	≥7.5
N30UH	1.08-1.13	10.8-11.3	≥796	≥10.0	≥1990	≥25	223-255	28-31	≤180	≥7.5
N33UH	1.14-1.18	11.4-11.8	≥852	≥10.5	≥1990	≥25	247-279	31-35	≤180	≥7.5
N35UH	1.17-1.24	11.7-12.4	≥876	≥11.0	≥1990	≥25	263-295	33-37	≤180	≥7.5
N38UH	1.23-1.29	12.3-12.9	≥915	≥11.5	≥1990	≥25	287-318	36-40	≤180	≥7.5
N40UH	1.26-1.32	12.6-13.2	≥939	≥11.8	≥1990	≥25	302-334	38-42	≤180	≥7.5
N42UH	1.28-1.35	12.8-13.5	≥963	≥12.1	≥1990	≥25	310-350	39-44	≤180	≥7.5
N45UH	1.32-1.38	13.2-13.8	≥987	≥12.4	≥1990	≥25	334-366	42-46	≤180	≥7.5
N48UH	1.37-1.42	13.7-14.2	≥1019	≥12.8	≥1910	≥24	358-390	45-49	≤180	≥7.5
N30EH	1.08-1.15	10.8-11.5	≥812	≥10.2	≥2388	≥30	223-255	28-32	≤200	≥7.5
N33EH	1.14-1.21	11.4-12.1	≥851	≥10.7	≥2388	≥30	247-279	31-35	≤200	≥7.5
N35EH	1.17-1.24	11.7-12.4	≥876	≥11.0	≥2388	≥30	263-295	33-37	≤200	≥7.5
N38EH	1.23-1.29	12.3-12.9	≥915	≥11.5	≥2388	≥30	287-318	36-40	≤200	≥7.5
N40EH	1.26-1.32	12.6-13.2	≥939	≥11.8	≥2388	≥30	302-334	38-42	≤200	≥7.5
N42EH	1.28-1.35	12.8-13.5	≥963	≥12.1	≥2388	≥30	310-350	39-44	≤200	≥7.5
N45EH	1.33-1.38	13.3-13.8	≥995	≥12.5	≥2308	≥29	334-366	42-46	≤200	≥7.5
N28AH	1.04-1.12	10.4-11.2	≥772	≥9.7	≥2786	≥35	207-239	26-30	≤230	≥7.5
N30AH	1.08-1.15	10.8-11.5	≥812	≥10.2	≥2786	≥35	223-255	28-32	≤230	≥7.5
N33AH	1.14-1.21	11.4-12.1	≥852	≥10.7	≥2786	≥35	247-279	31-35	≤230	≥7.5
N35AH	1.17-1.24	11.7-12.4	≥876	≥11.0	≥2786	≥35	263-295	33-37	≤230	≥7.5
N38AH	1.23-1.27	12.3-12.7	≥923	≥11.6	≥2786	≥35	287-318	36-40	≤230	≥7.5
N40AH	1.26-1.31	12.6-13.1	≥939	≥11.8	≥2628	≥33	302-334	38-42	≤230	≥7.5
N42AH	1.29-1.35	12.9-13.5	≥955	≥12.0	≥2628	≥33	318-350	40-44	≤230	≥7.5

to be continued(接下页)

杭州科德磁业有限公司

HANGZHOU KEDE MAGNETICS COMPONENTS CO., LTD.

中国浙江省杭州市桐庐县樟青塘路168号, 邮编: 311500

No.168 Zhangqingtang Road, Tonglu, Hangzhou 311500, China.

电话/tel: +86 571 64242689 传真/fax: +86 571 64242687,

电子邮件/email: info@kedemagnetics.com

KEDE

Typical Magnetic Properties of Sintered NdFeB Magnets (烧结钕铁硼磁铁典型磁性能表)

牌号 Grade	剩磁 Remanence induction		矫顽力 Coercive force		内禀矫顽力 Intrinsic Coercive force		最大磁能积 Maximum Energy product		工作温度 Working Temperature	密度 Density
	B _r		H _{cB}		H _{cJ}		(BH) _{max}		T _w	ρ
	T	KGs	KA/m	KOe	KA/m	KOe	KJ/m ³	MGOe	°C	g/cm ³
扩散工艺 Diffusion Process										
G48SH	1.37-1.42	13.7-14.2	≥1011	≥13	≥1592	≥20	358-390	45-49	≤150	≥7.5
G50SH	1.40-1.45	14.0-14.5	≥1027	≥13.2	≥1592	≥20	374-406	47-51	≤150	≥7.5
G52SH	1.42-1.48	14.2-14.8	≥1067	≥13.4	≥1592	≥20	390-422	49-53	≤150	≥7.5
G55SH	1.46-1.51	14.6-15.1	≥1083	≥13.6	≥1592	≥20	406-438	51-55	≤150	≥7.5
G45UH	1.33-1.38	13.3-13.8	≥978	≥12.4	≥1990	≥25	334-366	42-46	≤180	≥7.5
G48UH	1.37-1.42	13.7-14.2	≥1027	≥12.9	≥1990	≥25	358-390	45-49	≤180	≥7.5
G50UH	1.40-1.45	14.0-14.5	≥1051	≥13.2	≥1990	≥25	374-406	47-51	≤180	≥7.5
G52UH	1.42-1.48	14.2-14.8	≥1067	≥13.4	≥1990	≥25	390-422	49-53	≤180	≥7.5
G54UH	1.46-1.51	14.6-15.1	≥1075	≥13.5	≥1990	≥25	406-438	51-55	≤180	≥7.5
G40EH	1.26-1.31	12.6-13.1	≥955	≥12.0	≥2388	≥30	302-334	38-42	≤200	≥7.5
G44EH	1.29-1.35	12.9-13.5	≥971	≥12.2	≥2388	≥30	318-350	40-44	≤200	≥7.5
G46EH	1.33-1.38	13.3-13.8	≥1011	≥12.7	≥2388	≥30	334-366	42-46	≤200	≥7.5
G48EH	1.37-1.42	13.7-14.2	≥1027	≥12.9	≥2388	≥30	358-390	45-49	≤200	≥7.5
G50EH	1.40-1.45	14.0-14.5	≥1051	≥13.2	≥2308	≥29	374-406	47-51	≤200	≥7.5